

TECHNICAL DATA SHEET

PLAST320L - 585 ‰

Master alloy for the production of yellow 375 - 417 - 585 - 750 - 875 - 917 ‰ gold jewellery obtained by mechanical working. The elements contained in this product ensure a high surface quality and a high deformation capability thanks the small grain structure, making it suitable for the production of hand and machine made hollow and solid chains, deep drawn items and tube.

TAB.1 - Mechanical data

Hardness as cast	141	HV
Hardness hardened	194	HV
Tensile strength	466	MPa
Yield strength	271	MPa
Elongation	43	%

TAB.2 - Physical data

Color	Hamilton yellow		
Colour Coordinates	L*:	89.51	
	a*:	2.69	
	b*:	19.24	
Density	12.92	g/cm ³	
Melting Range	Solidus:	814	°C
	Liquidus:	865	°C

TAB.3 - Heat treatments

Solution annealing	675 20	°C min
Recrystallization Annealing	675 20	°C min
Hardening	275 180	°C min

TAB.4 - Mechanical working parameters

Premelting temperature		965	°C
Casting Temperature	Min:	915	°C
	Max:	1015	°C
First thickness reduction	Lamination:	50	%
	Drawing:	25	%
Following thickness reductions	Lamination:	75	%
	Drawing:	50	%
Pickling after annealing	H2SO4:	20	%
	Temp:	50	°C
	Time:	5	min