

TECHNICAL DATA SHEET

PLAST323L - 917 ‰

Master alloy for the production of yellow 375 - 417 - 585 - 750 - 875 - 917 ‰ gold jewellery obtained by mechanical working. The elements contained in this product ensure a high surface quality and a high deformation capability thanks the small grain structure, making it suitable for the production of hand and machine made hollow and solid chains, deep drawn items and tube.

TAB.1 - Mechanical data

Hardness as cast	82	HV
Hardness hardened	n.d.	
Tensile strength	n.d.	
Yield strength	n.d.	
Elongation	n.d.	

TAB.2 - Physical data

Color	Deep yellow		
Colour Coordinates	L*:	87.06	
	a*:	7.48	
	b*:	25.42	
Density	17.08	g/cm ³	
Melting Range	Solidus:	912	°C
	Liquidus:	958	°C

TAB.3 - Heat treatments

Solution annealing	675	°C
	20	min
Recrystallization Annealing	675	°C
	20	min
Hardening	n.d.	

TAB.4 - Mechanical working parameters

Premelting temperature		1058	°C
Casting Temperature	Min:	1008	°C
	Max:	1108	°C
First thickness reduction	Lamination:	50	%
	Drawing:	25	%
Following thickness reductions	Lamination:	75	%
	Drawing:	50	%
Pickling after annealing	H2SO4:	20	%
	Temp:	50	°C
	Time:	5	min