

TECHNICAL DATA SHEET

PRIMA311L - 375 ‰

Master alloy for the production of yellow 375 - 417 - 585 ‰ gold jewellery obtained by investment casting. This product, thanks to its complex composition made of numerous different special elements, ensures an extreme level of deoxidation, an extreme surface quality, an enhanced fluidity and a long lasting of this features also after many reuses of casting scraps, making it the most advanced solution for castings with and without stones in place.

TAB.1 - Mechanical data

Hardness as cast	104	HV
Hardness hardened	n.d.	
Tensile strength	331	MPa
Yield strength	140	MPa
Elongation	52	%

TAB.2 - Physical data

Color	Deep yellow		
Colour Coordinates	L*:	91.22	
	a*:	1.74	
	b*:	18.95	
Density	10.95	g/cm ³	
Melting Range	Solidus:	835	°C
	Liquidus:	907	°C

TAB.3 - Heat treatments

Solution annealing	626 20	°C min
Recrystallization Annealing	626 20	°C min
Hardening	275	°C
	180	min

TAB.4 - Investment casting parameters

Premelting temperature		1007	°C
Casting Temperature	Min: Max:	957 1057	°C °C
Water investment powder ratio		36-38	%
Flask temperature	Min: Max:	450 700	°C °C
Quenching time without stones in place	Min: Max:	5 20	min min
Quenching time with stones in place		15	min in boiling water
Pickling	H2SO4: Temp: Time:	20 50 50	% °C min