

TECHNICAL DATA SHEET

SPARK311L - 375 ‰

Master alloy for the production of yellow 375 - 417 - 585 ‰ gold jewellery obtained by investment casting. The elements contained in this product ensure a high deoxidation in casting and a high surface quality, making it suitable for castings with and without stones in place.

TAB.1 - Mechanical data

Hardness as cast	104	HV
Hardness hardened	n.d.	
Tensile strength	350	MPa
Yield strength	152	MPa
Elongation	51	%

TAB.2 - Physical data

Color	Deep yellow		
Colour Coordinates	L*:	89.70	
	a*:	3.61	
	b*:	18.4	
Density	11.07	g/cm ³	
Melting Range	Solidus:	849	°C
	Liquidus:	915	°C

TAB.3 - Heat treatments

Solution annealing	675 20	°C min
Recrystallization Annealing	675 20	°C min
Hardening	275	°C
	180	min

TAB.4 - Investment casting parameters

Premelting temperature		1015	°C
Casting Temperature	Min:	965	°C
	Max:	1065	°C
Water investment powder ratio		36-38	%
Flask temperature	Min:	450	°C
	Max:	700	°C
Quenching time without stones in place	Min:	5	min
	Max:	20	min
Quenching time with stones in place		15	min in boiling water
Pickling	H2SO4:	20	%
	Temp:	50	°C
	Time:	50	min