

TECHNICAL DATA SHEET

STAR752 - 750 ‰

Universal master alloy for the production of white palladium based 750 ‰ gold jewellery obtained by investment casting and mechanical working. The elements contained in this product ensure a high surface quality in investment casting, while in mechanical working a high deformation capability thanks the small grain structure, making it suitable for the production of hand and machine made hollow and solid chains, deep drawn items and tube.

TAB.1 - Mechanical data

Hardness as cast	101	HV
Hardness hardened	n.d.	
Tensile strength	355	MPa
Yield strength	170	MPa
Elongation	31	%

TAB.2 - Physical data

Color	Premium white		
Colour Coordinates	L*:	80.31	
	a*:	2.09	
	b*:	9.04	
Density	16.12	g/cm ³	
Melting Range	Solidus:	925	°C
	Liquidus:	1124	°C

TAB.3 - Heat treatments

Solution annealing	800 30	°C min
Recrystallization Annealing	800 30	°C min
Hardening	n.d.	

TAB.4 - Investment casting parameters

Premelting temperature		1224	°C
Casting Temperature	Min:	1174	°C
	Max:	1274	°C
Water investment powder ratio		36-38	%
Flask temperature	Min:	600	°C
	Max:	720	°C
Quenching time without stones in place	Min:	5	min
	Max:	20	min
Quenching time with stones in place		15	min in boiling water
Pickling	H2SO4:	20	%
	Temp:	50	°C
	Time:	50	min

TAB.5 - Mechanical working parameters

Premelting temperature		1224	°C
Casting Temperature	Min:	1174	°C
	Max:	1274	°C
First thickness reduction	Lamination:	50	%
	Drawing:	25	%
Following thickness reductions	Lamination:	75	%
	Drawing:	50	%
Pickling after annealing	H2SO4:	20	%
	Temp:	50	°C
	Time:	5	min